

ORAJET® 3621 PVC económico calendrado

Descripción

4 años, 3 mil película de PVC económica calandrada para la impresión a base solvente.

Papel de desprendimiento

Papel con recubrimiento de PE, 78#

Adhesivo

Gris, a base de agua, adhesivo removible

Areas of uso

Grado económico y superficies planas, para aplicaciones a corto o mediano plazo que necesitan ser removidas fácilmente, tales como billboards y señalizaciones en tránsito.

Datos técnicos:

| | |
|---|---|
| Espesor (sin adhesivo ni liner) | 3 mil |
| Estabilidad dimensional (FINAT – TM 14) | adherido al acero, no hay encogimiento en dirección transversal, a lo largo, < 0.016" |
| Seawaterability (DIN 50 021) | Adhered to aluminum, after 100 h / 73°F no variation. |
| Resistencia a la temperatura | adherido al aluminio, -40 °F a +176 °F, sin variación |
| Conducta ante fuego (DIN 75200) | adherido al acero, se autoestingue |
| Poder de adhesión (FINAT TM-1, luego de 24 h, acero inoxidable) | mín. 3.7 lb/pul. |
| Tensile Strength (DIN EN ISO 527) Along Across | min. 19 MPa min. 19 MPa |
| Elongation at break (DIN EN ISO 527) Along Across | min. 130% min. 150% |
| Shelf life (68°F/ 50% relative humidity) | 2 years |
| Minimum Application Temperature | + 50°F |
| Available Lengths | 164' (50 meters), 100 meter and 250 meter roll lengths are available upon request for 60" and 80" |
| Available Widths | 54", 60", 80" |
| Minimum Life by Application Specialist under vertical outdoor exposure | 4 years |

Attention:

Surfaces to which the material will be applied must be cleaned thoroughly of dust, grease or any contaminants. Freshly lacquered or painted surfaces should be allowed to stand for at least three weeks after complete curing. The compatibility of selected lacquers and paints should be tested by the end-user prior to use.

The statements in this information sheet are based upon our knowledge and practical experience. This data is intended only as a source of information and is given without any guarantee and does not constitute a warranty. Due to the wide variety of possible uses and applications, customers should independently determine the suitability of this material for their specific purpose, prior to use.



ORACAL USA
A DIVISION OF LIG INTERNATIONAL, INC.
7251 Salisbury Road
Jacksonville, FL 32256 USA
Toll Free 888.672.2251
904.726.9597 • FAX 904.726.9409
www.oracal.com • Oracal USA © 2003

ORAJET[®] 3621 Recommended Printers

Solvent-based Printers:

Encad: VinylJet 36

Oce: Arizona 30/90/180/500

Mutoh: Toucan, Falcon Outdoor, Falcon Outdoor II

Mimaki: JV3

Nur: Fresco, Salsa, Blueboard

Roland: VersaCamm SP-300, Sol-Jet Pro 540 EX, Sol-Jet II

Scitex: Idanit Novo, Grandjet, Press Jet

Seiko: ColorPainter 64S

Vutek: Press Vu, Ultra Vu 3000/3300, Ultra Vu 5000/5300, Ultra Vu 2360 SC, Ultra Vu 3360 SC

DGI: VT-11 62, VT-11 92, VT-100D

Gerber: Orion, Tomahawk